

LNP™ THERMOCOMP™ COMPOUND DX10311

REGION ASIA

DESCRIPTION

DX10311 is 30% glass fiber reinforced, impact modified polycarbonate resin. High flow and good ductility.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	117	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	8330	MPa	ASTM D 638
Flexural Stress	190	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	119	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.7	%	ISO 527
Tensile Modulus, 1 mm/min	8260	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	182	MPa	ISO 178
Flexural Stress, break, 2 mm/min	181	MPa	ISO 178
Flexural Modulus, 2 mm/min	7720	MPa	ISO 178
IMPACT			
Charpy Impact, unnotched, 23°C	57	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	752	J/m	ASTM D 4812
Izod Impact, notched, 23°C	196	J/m	ASTM D 256
Charpy Impact, notched, 23°C	20	kJ/m ²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	128	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.9E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.4E-05	1/°C	ASTM E 831
PHYSICAL			
Specific Gravity	1.42	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm (5)	0.1 – 0.3	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm (5)	0.2 – 0.4	%	SABIC method
Melt Volume Rate, MVR at 300°C/5.0 kg	37	cm ³ /10 min	ISO 1133
MECHANICAL PROPERTIES			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Flexural modulus	7670	MPa	ISO 178/1A
INJECTION MOLDING			
Drying Temperature	90 – 110	°C	
Drying Time	3 – 5	hrs	
Melt Temperature	280 – 320	°C	
Nozzle Temperature	280 – 320	°C	
Front - Zone 3 Temperature	280 – 320	°C	
Middle - Zone 2 Temperature	280 – 320	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Mold Temperature	90 – 120	°C	
Back Pressure	1 – 5	MPa	
Screw Speed	30 – 100	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.