

LNP™ THERMOCOMP™ COMPOUND 5C003

FP-VC-1003
REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP* 5C003 is a compound based on Polyvinylidene Fluoride resin containing 15% Carbon Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	78	MPa	ASTM D 638
Tensile Strain, break	0.8	%	ASTM D 638
Tensile Modulus, 50 mm/min	14270	MPa	ASTM D 638
Flexural Stress	127	MPa	ASTM D 790
Tensile Stress, break	67	MPa	ISO 527
Tensile Strain, break	0.6	%	ISO 527
Tensile Modulus, 1 mm/min	14500	MPa	ISO 527
Flexural Stress	147	MPa	ISO 178
Flexural Modulus	20920	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	202	J/m	ASTM D 4812
Izod Impact, notched, 23°C	58	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	11	J	ASTM D 3763
Multiaxial Impact	3	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	14	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	165	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	159	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.13E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.62E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	3.13E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.62E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	156	°C	ISO 75/Af
PHYSICAL			
Density	1.769	g/cm ³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.03	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs (5)	0.3 – 0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	1 – 1.3	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.36	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	1.16	%	ISO 294
Density	1.76	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
MECHANICAL PROPERTIES			
Flexural modulus	11790	MPa	ISO 178/1A
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Melt Temperature	215 – 230	°C	
Front - Zone 3 Temperature	225 – 245	°C	
Middle - Zone 2 Temperature	210 – 225	°C	
Rear - Zone 1 Temperature	190 – 210	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.