

# CYCOLAC™ RESIN INP338

REGION AMERICAS

## DESCRIPTION

SABIC INP338 is an ultra high rubber ABS impact modifier resin, and is based on polybutadiene rubber. Offers superior impact efficiency, especially at low temperatures. Reduces notch sensitivity when alloyed with engineering polymers. Disperses easily. Provides abrasion and chemical resistance to polymers. Provides toughness to PVC sheet, profile, electrical conduit and injection molded applications. Increases the impact strength of recycle PVC and other recyclates. Can be blended with polyurethanes and other polymers for improved performance and economics. Can be used to improve the impact performance of PC, polyesters, and CPVC. Powder. FDA compliant (part use must be at room temperature or below).

## TYPICAL PROPERTY VALUES

Revision 20180514

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Hardness, Shore D	40	-	ASTM D 2240
<b>PHYSICAL</b>			
Specific Gravity	0.95	-	ASTM D 792
Melt Flow Rate, 200°C/3.8 kgf	5.7	g/10 min	ASTM D 1238
Density (Molded)	0.96	g/cm <sup>3</sup>	ISO 1183
Mean Resin Particle Size	180	micrometer	SABIC method
Total NA Volatiles	0.3	%	SABIC method
BD	70	%	SABIC method
Bulk Density	0.25	g/cm <sup>3</sup>	ASTM D 1895

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.