

# CHIMEI 奇美實業股份有限公司 CHI MEI CORPORATION

59-1, San Chia, Jen Te, Tainan County, Taiwan TEL: 06-266-3000 FAX: 06-266-9069

## SPECIFICATION

ITEM	METHOD	Condition	Unit	PG-383D
MFR 流動指數	ISO 1133	200°C*5kg	ml/10 min	2.5
SP 軟化點	ISO 306	1Kg,50°C/Hr	°C	106
TSy 引張強度	ISO 527	50 mm/min	M Pa	54
EL 延伸率	ISO 527	50 mm/min	%	6
FM 彎曲彈性率	ISO 178	2 mm/min	G Pa	82
FS 彎曲強度	ISO 178	2 mm/min	M Pa	82
透光率	-	-	-	89%
折射率	-	-	-	1.587
粒子YI	ASTM E-308	-	-	-2.00

\* Physical properties by Analysis Department of Chimei Corp.