

► BI720

# PP

Low gloss / High flow impact copolymer for Injection Molding

### Description

**BI720** is a high flow impact copolymer designed to have low gloss compared to the conventional PP products. Due to its low gloss and high flowability, it can be an excellent candidate for the base resin of PP composite for the interior parts of automobile.

#### **Characteristics**

- Low gloss  $\rightarrow$  Interior part of automobile
- High flowability  $\rightarrow$  Large-size injection molded products

#### Applications

• Automobile compound articles: instrumental panel, door trim, etc

<b>Typical Properties</b>	Method (ASTM)	Unit	BI720
Melt flow index	D1238	g/10min	30
Density	D1505	g/cm <sup>3</sup>	0.91
Tensile strength at yield	D638	kg/cm <sup>2</sup>	250
Elongation at break	D638	%	60
Flexural modulus	D790	kg/cm <sup>2</sup>	13,000
Izod impact strength at 23 $^\circ \rm C$ -20 $^\circ \rm C$	D256	kgcm/cm	7.0 4.0
Rockwell hardness	D785	R-scale	85
Heat distortion temp.	D648	°C	110
Gloss (60 <sup>°</sup> )	D2457	%	57

## Physical Properties

\* Data performed by or on behalf of Hanwha Total <u>www.cn-plas.com</u>



#### Food Contact Application

- ► There may be some limitation to apply Hanwha Total BI720 to the food packaging. Thus, the verification on the suitability is necessary.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.

#### **Contacts**

Product Information & Technical Services <u>www.cn-plas.com</u>

#### Disclaimer

This <u>www.cn-plas.com</u> document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE

GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.

> LTE21016 2 / 2