

# VALOX<sup>TM</sup> RESIN SHF4320

REGION EUROPE

## DESCRIPTION

VALOX SHF4320 is a 10% glass fibre reinforced PBT injection moulding resin with excellent flow combined with good mechanical and heat properties.  
Applications: Automotive connectors.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield, 5 mm/min	90	MPa	ISO 527
Tensile Stress, break, 5 mm/min	90	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.4	%	ISO 527
Tensile Strain, break, 5 mm/min	3.4	%	ISO 527
Tensile Modulus, 1 mm/min	4550	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	130	MPa	ISO 178
Flexural Stress, break, 2 mm/min	130	MPa	ISO 178
Flexural Strain, break, 2 mm/min	5	%	ISO 178
Flexural Modulus, 2 mm/min	4000	MPa	ISO 178
Hardness, H358/30	110	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
<b>IMPACT</b>			
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	25	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
Vicat Softening Temp, Rate A/50	220	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	215	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.63E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	4.79E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	2.11E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/120	205	°C	ISO 306

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	215	°C	ISO 75 /Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	185	°C	ISO 75 /Af
<b>PHYSICAL</b>			
Specific Gravity	1.36	-	ASTM D 792
Filler Content	10	%	ASTM D 229
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.9	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.7 – 1.1	%	SABIC method
Density	1.36	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	28	cm <sup>3</sup> /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	100	Pa-s	ISO 11443
<b>ELECTRICAL</b>			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.4	-	ASTM D 150
Dissipation Factor, 1 MHz	0.015	-	ASTM D 150
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	30	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	23	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.4	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.015	-	IEC 60250
Comparative Tracking Index	325	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.1	-	IEC 60250
<b>FLAME CHARACTERISTICS</b>			
UL Compliant, 94HB Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 750°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	750	°C	IEC 60695-2-13
<b>INJECTION MOLDING</b>			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.