

# VALOX<sup>TM</sup> RESIN V8030CS

REGION AMERICAS

## DESCRIPTION

Dual processable for use in cooking appliance components such as gas-assist molded handles and injection molded end caps

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	99	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	98	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	2.7	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.8	%	ASTM D 638
Nominal Strain, brk, 5 mm/min	8.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	6170	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	148	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	148	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5580	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	95	MPa	ISO 527
Tensile Stress, break, 5 mm/min	103	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.1	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	5880	MPa	ISO 527
Flexural Stress	148	MPa	ISO 178
Flexural Strain, break, 2 mm/min	3.4	%	ISO 178
Flexural Modulus	5480	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	58	J/m	ASTM D 256
Izod Impact, notched 80°10'4 +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Charpy Impact, notched, 23°C, 80°10'4mm, Cut	23	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL</b>			
Vicat Softening Temp, Rate A/50	224	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm	220	°C	ASTM D 648
HDT, 1.82 MPa, 3.2 mm	173	°C	ASTM D 648
Vicat Softening Temp, Rate A/50	222	°C	ISO 306
Vicat Softening Temp, Rate A/120	222	°C	ISO 306
<b>PHYSICAL</b>			
Density	1.43	g/cm <sup>3</sup>	ASTM D 792
Density	1.43	g/cm <sup>3</sup>	ISO 1183
Melt Volume Rate, MVR at 265°C/2.16 kg	29	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	75	cm <sup>3</sup> /10 min	ISO 1133



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.