

VALOXTM RESIN VX4930

REGION EUROPE

DESCRIPTION

VALOX VX4930 is a 30% glass reinforced nucleated PBT/ASA blend with excellent mechanical properties, high dimensional stability and low density. Applications: connectors and automotive industry.

TYPICAL PROPERTY VALUES

Revision 20190214

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|--------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 5 mm/min | 125 | MPa | ASTM D 638 |
| Tensile Stress, brk, Type I, 5 mm/min | 125 | MPa | ASTM D 638 |
| Tensile Strain, yld, Type I, 5 mm/min | 2.8 | % | ASTM D 638 |
| Tensile Strain, brk, Type I, 5 mm/min | 2.8 | % | ASTM D 638 |
| Tensile Modulus, 5 mm/min | 9500 | MPa | ASTM D 638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 175 | MPa | ASTM D 790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 7700 | MPa | ASTM D 790 |
| Taber Abrasion, CS-17, 1 kg | 65 | mg/1000cy | SABIC method |
| Tensile Stress, yield, 5 mm/min | 130 | MPa | ISO 527 |
| Tensile Stress, break, 5 mm/min | 130 | MPa | ISO 527 |
| Tensile Strain, yield, 5 mm/min | 2.8 | % | ISO 527 |
| Tensile Strain, break, 5 mm/min | 2.8 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 9600 | MPa | ISO 527 |
| Flexural Stress, yield, 2 mm/min | 185 | MPa | ISO 178 |
| Flexural Stress, break, 2 mm/min | 180 | MPa | ISO 178 |
| Flexural Strain, break, 2 mm/min | 2.9 | % | ISO 178 |
| Flexural Modulus, 2 mm/min | 8200 | MPa | ISO 178 |
| Hardness, H358/30 | 210 | MPa | ISO 2039-1 |
| Hardness, Rockwell R | 116 | - | ISO 2039-2 |
| IMPACT | | | |
| Charpy Impact, unnotched, 23°C | 55 | kJ/m ² | ISO 179/2C |
| Charpy Impact, unnotched, -30°C | 45 | kJ/m ² | ISO 179/2C |
| Izod Impact, unnotched, 23°C | 800 | J/m | ASTM D 4812 |
| Izod Impact, unnotched, -30°C | 800 | J/m | ASTM D 4812 |
| Izod Impact, notched, 23°C | 80 | J/m | ASTM D 256 |
| Izod Impact, notched, 0°C | 80 | J/m | ASTM D 256 |
| Izod Impact, notched, -30°C | 80 | J/m | ASTM D 256 |
| Instrumented Impact Total Energy, 23°C | 78 | J | ASTM D 3763 |
| Izod Impact, unnotched 80*10*4 +23°C | 50 | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*4 -30°C | 45 | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*4 +23°C | 9 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*4 0°C | 8 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*4 -30°C | 8 | kJ/m ² | ISO 180/1A |
| Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm | 7 | kJ/m ² | ISO 179/1eA |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|----------------|-------------------------|----------------|
| Charpy Impact, notched, 23°C | 9 | kJ/m ² | ISO 179/2C |
| Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm | 6 | kJ/m ² | ISO 179/1eA |
| Charpy Impact, notched, -30°C | 9 | kJ/m ² | ISO 179/2C |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | 30 | kJ/m ² | ISO 179/1eU |
| Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm | 25 | kJ/m ² | ISO 179/1eU |
| THERMAL | | | |
| Vicat Softening Temp, Rate A/50 | 218 | °C | ASTM D 1525 |
| Vicat Softening Temp, Rate B/50 | 182 | °C | ASTM D 1525 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 190 | °C | ASTM D 648 |
| CTE, -40°C to 40°C, flow | 2.2E-05 | 1/°C | ASTM E 831 |
| CTE, -40°C to 40°C, xflow | 1.15E-04 | 1/°C | ASTM E 831 |
| Thermal Conductivity | 0.26 | W/m-°C | ISO 8302 |
| CTE, 23°C to 60°C, flow | 2.2E-05 | 1/°C | ISO 11359-2 |
| CTE, 23°C to 60°C, xflow | 1.15E-04 | 1/°C | ISO 11359-2 |
| Ball Pressure Test, 125°C +/- 2°C | PASSES | - | IEC 60695-10-2 |
| Vicat Softening Temp, Rate A/50 | 218 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/50 | 182 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 182 | °C | ISO 306 |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm | 215 | °C | ISO 75/Be |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm | 190 | °C | ISO 75/Ae |
| Relative Temp Index, Elec | 50 | °C | UL 746B |
| Relative Temp Index, Mech w/impact | 50 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact | 50 | °C | UL 746B |
| PHYSICAL | | | |
| Specific Gravity | 1.46 | - | ASTM D 792 |
| Filler Content | 30 | % | ASTM D 229 |
| Mold Shrinkage on Tensile Bar, flow | 0.1 – 0.3 | % | SABIC method |
| Mold Shrinkage, flow, 3.2 mm | 0.3 – 0.7 | % | SABIC method |
| Mold Shrinkage on Tensile Bar, xflow | 0.3 – 0.7 | % | SABIC method |
| Melt Flow Rate, 200°C/3.8 kgf | 13 | g/10 min | ASTM D 1238 |
| Melt Flow Rate, 265°C/5.0 kgf | 35 | g/10 min | ASTM D 1238 |
| Melt Flow Rate, 266°C/5.0 kgf | 35 | g/10 min | ASTM D 1238 |
| Density | 1.46 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/sat) | 0.71 | % | ISO 62 |
| Moisture Absorption (23°C / 50% RH) | 0.23 | % | ISO 62 |
| Melt Volume Rate, MVR at 250°C/5.0 kg | 13 | cm ³ /10 min | ISO 1133 |
| Melt Volume Rate, MVR at 265°C/5.0 kg | 25 | cm ³ /10 min | ISO 1133 |
| Melt Viscosity, 260°C, 1500 sec-1 | 130 | Pa-s | ISO 11443 |
| ELECTRICAL | | | |
| Comparative Tracking Index (UL) {PLC} | 1 | PLC Code | UL 746A |
| Volume Resistivity | >1.E+15 | Ohm-cm | IEC 60093 |
| Surface Resistivity, ROA | >1.E+15 | Ohm | IEC 60093 |
| Dielectric Strength, in oil, 3.2 mm | 21 | kV/mm | IEC 60243-1 |
| Relative Permittivity, 1 MHz | 3.2 | - | IEC 60250 |
| Dissipation Factor, 50/60 Hz | 0.0024 | - | IEC 60250 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------|----------------|
| Dissipation Factor, 1 MHz | 0.0182 | - | IEC 60250 |
| Comparative Tracking Index | 500 | V | IEC 60112 |
| Relative Permittivity, 50/60 Hz | 3.6 | - | IEC 60250 |
| FLAME CHARACTERISTICS | | | |
| UL Recognized, 94HB Flame Class Rating | 0.75 | mm | UL 94 |
| UL Recognized, 94HB Flame Class Rating 2nd value | 3 | mm | UL 94 |
| Glow Wire Flammability Index 750°C, passes at | 1 | mm | IEC 60695-2-12 |
| INJECTION MOLDING | | | |
| Drying Temperature | 110 – 120 | °C | |
| Drying Time | 2 – 4 | hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 250 – 270 | °C | |
| Nozzle Temperature | 240 – 260 | °C | |
| Front - Zone 3 Temperature | 245 – 265 | °C | |
| Middle - Zone 2 Temperature | 240 – 255 | °C | |
| Rear - Zone 1 Temperature | 230 – 245 | °C | |
| Hopper Temperature | 40 – 60 | °C | |
| Mold Temperature | 40 – 100 | °C | |

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.