

# LNP<sup>TM</sup> LUBRICOMP<sup>TM</sup> COMPOUND EX00548C

PDX-E-00548 CCS

## DESCRIPTION

LNP<sup>TM</sup> LUBRICOMP<sup>TM</sup> EX00548C is a compound based on Polyetherimide resin containing Proprietary Fillers. Added features of this material include: Clean Compounding System, Wear Resistant.

## TYPICAL PROPERTY VALUES

Revision 20201123

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yield	85	MPa	ASTM D 638
Tensile Stress, break	83	MPa	ASTM D 638
Tensile Strain, yield	6.1	%	ASTM D 638
Tensile Strain, break	8.1	%	ASTM D 638
Tensile Modulus, 50 mm/min	3030	MPa	ASTM D 638
Flexural Stress	148	MPa	ASTM D790
Flexural Modulus	3440	MPa	ASTM D790
Tensile Stress, yield	86	MPa	ISO 527
Tensile Stress, break	85	MPa	ISO 527
Tensile Strain, yield	6	%	ISO 527
Tensile Strain, break	7.6	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress	143	MPa	ISO 178
Flexural Modulus	3390	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	469	J/m	ASTM D4812
Izod Impact, notched, 23°C	26	J/m	ASTM D 256
Instrumented Dart Impact Energy @ peak, 23°C	4	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	32	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL</b>			
HDT, 1.82 MPa, 3.2mm, unannealed	185	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	184	°C	ISO 75/Af
Relative Temp Index, Elec <sup>(1)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	105	°C	UL 746B
<b>PHYSICAL</b>			
Density	1.31	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.22	%	ASTM D570
Mold Shrinkage, flow, 24 hrs	0.7	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs	0.7	%	ASTM D955
Mold Shrinkage, flow, 24 hrs	0.66	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.7	%	ISO 294
Density	1.31	g/cm <sup>3</sup>	ISO 1183

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-101345280</a>	-	-
UL Yellow Card Link 2	<a href="#">E207780-101345235</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	0.35	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	360 – 375	°C	
Rear - Zone 1 Temperature	355 – 365	°C	
Middle - Zone 2 Temperature	360 – 370	°C	
Front - Zone 3 Temperature	365 – 375	°C	
Nozzle Temperature	365 – 375	°C	
Mold Temperature	140 – 180	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw speed (Circumferential speed)	0.2 – 0.3	m/s	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.