

LNP™ THERMOCOMP™ COMPOUND DX05477

DFA-113 EM MR
REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP* DX05477 is a compound based on Polycarbonate resin containing Glass Fiber. Added features of this material include: Easy Molding, Mold Release, Flame Retardant.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	62	MPa	ASTM D 638
Tensile Stress, break	57	MPa	ASTM D 638
Tensile Strain, yield	4.2	%	ASTM D 638
Tensile Strain, break	7.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	2820	MPa	ASTM D 638
Flexural Stress	119	MPa	ASTM D 790
Tensile Stress, yield	70	MPa	ISO 527
Tensile Stress, break	69	MPa	ISO 527
Tensile Strain, yield	3.8	%	ISO 527
Tensile Strain, break	4.4	%	ISO 527
Tensile Modulus, 1 mm/min	3600	MPa	ISO 527
Flexural Stress	120	MPa	ISO 178
Flexural Modulus	3700	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	96	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	5	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	145	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	138	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Af
PHYSICAL			
Density	1.271	g/cm ³	ASTM D 792

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 24 hrs (5)	0.5	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.6	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs (5)	0.5	%	ISO 294
Mold Shrinkage, xflow, 24 hrs (5)	0.59	%	ISO 294
Density	1.26	g/cm ³	ISO 1183
MECHANICAL PROPERTIES			
Flexural modulus	3440	MPa	ISO 178/1A
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.